

## RCxx30 WAX EFFECT TOPCOAT

Protection-Finishing-Maintenance

**Field of application:** doors and windows, garden furniture, coverings, balconies, enclosures, beams.

**Information:** this coating is soft to the touch. It makes the wood water-repellent, resistant and durable. It enhances the natural matt aspect.

### Instructions

*Stained/impregnated wood.* It is possible to apply RCxx30 on a wood treated with low-solid content dyes or impregnating stains. Once the surface has been cleaned, sand with sandpaper or scotch brite. Then remove the powder and apply 1-2 coats of product.

*Coated wood.* On a paint finish that is in good condition it is necessary to sand with 320 grit sandpaper. Clean the surface, then proceed to paint. On a paint finish that is in bad condition, sand with 80-150 grit sandpaper to bring the wood back to the raw condition. Clean the surface and proceed to paint. Application of 1-2 coats of classic effect Impregnating stain RMxx10 before wax effect Topcoat RCxx30 is recommended.

**Maintenance:** in case of objects, which are very exposed to the atmospheric agents, it is sufficient to treat only the parts that begin to deteriorate. Slightly sand the object with 220-320 grit sandpaper, remove the powder and apply one coat of the desired colour. On the most deteriorated parts it is possible to apply a second coat. If the object is not much exposed to the atmospheric agents, the maintenance operations will be less frequent.

**Overcoating:** Topcoats of wax effect RCxx30 range.

**Packaging:** 0,75 L, 2,5 L, 5 L, 25 L.



Storage: at not less than 5°C



Painting: at not less than 10°C



Ready to use



Application:  
by brush or spray gun



Yield per coat:  
10 m<sup>2</sup>/L



Mix it well before  
use



Drying time between  
the coats: 2-6 hours



Final drying time:  
12 hours



**RC2030**  
TRANSPARENT



**RC3030**  
HONEY